UDS A02

10. (Twice Amended) A substrate according to any of claims 1, 42 or 43 wherein the sheet of plastic is PET.

11. (Twice Arhended) A substrate according to any of claims 1, 42 or 43 wherein the sheet of plastic is BOPP.

Contal

12. (Twice Amended) A substrate according to any of claims 1, 42 or 43 wherein the overlayer comprises styrene butadiene copolymer.

14. (Twice Amended) A substrate according to any of claims 1, 42 or 43, wherein the overlayer comprises ethylene acrylic acid copolymer.

- 19. (Twice Amended) A substrate according to any of claims I, 42 or 43 wherein the overlayer comprises polyvinyl pyridine.
- 20. (Twice Amended) A substrate according to any of claims 1, 42 or 43 wherein the underlayer comprises amine terminated polyamide.
- 21. (Twice Amended) A substrate according to any of claims 1, 42 or 43 wherein the underlayer comprises a silane coupling agent.
- 22. (Twice Amended) A substrate according to any of claims 1, 42 or 43 wherein the underlayer comprises amino propyl triethoxy silane.
- 23. (Twice Amended) A substrate according to any of claims 1, 42 or 43 wherein the underlayer has a weight of between 0.1 and 1 grams per square meter.
- 24. (Twice Amended) A substrate according to any of claims 1, 42 or 43 wherein the underlayer has a weight of between about 0.3 and 0.5 grams per square meter.

25. (Twice Amended) A substrate according to claim 1 wherein the overlayer has a weight of between 0.1 and 10 grams per square meter.

2

B4

5,1

UDS <u>A02</u>

Startid contid

26. (Twice Amended) A substrate according to claim 1 or claim 42 wherein the overlayer has a weight of between 0.2 and 2 grams per square meter.

5×15

- 28. (Twice Amended) A substrate according to any of claims 1, 42 or 43 wherein the underlayer is substantially free of particulate matter.
- 29. Twice Amended) A substrate according to any of claims 1, 42 or 43 comprising only two coating layers.

BOW

32. (Twice Amended) A substrate produced according to the method of claim 30 or claim 45

B 75%

37. (Twice Amended) A printing method comprising:

providing a substrate according to any of claims 1, 42 or 43 or produced according to claim 30 or claim 45; and

printing a toner image on the substrate.

42. (New) A substrate suitable for printing a toner image thereon, comprising:

a sheet of plastic;

461

an underlayer coating on the sheet of plastic, comprising a first polymer material comprising a polymer chosen from the group consisting of amine terminated polyamide, a silane coupling agent and amino propyl triethoxy silane; and

an overlayer coating, directly on the underlayer, comprising a second polymer material and having an outer surface to which a toner image can be fused and fixed,

wherein the overlayer coating has a thickness of between 0.1 and 10 microns.

- 43. (New) A substrate comprising a sheet of BOPP and an outer coating having a thickness of between 0.1 and 10 microns consisting substantially only of a polymer chosen from the group consisting of ethylene acrylic acid copolymer, and polyvinyl pyridine.
- 44. (New) A substrate according to claim 42 or claim 43 wherein the overlayer coating has a thickness of between 0.2 and 2 microns.
- 45. (New) A method of producing a coated substrate which a toner image can be adhered comprising:

3